



**WearGuard™ D-A SYN FQH Series** Food Grade synthetic multi-purpose oils are blended from 100% synthetic hydrocarbon (PAO) base oils, with additives that meet 1998 USDA H-1 requirements for incidental contact. **WearGuard™ D-A SYN FQH Series** meets all of the requirements of FDA Regulations 21 CFR 178.3570 and is registered with NSF.

## Applications

- Hydraulic Systems
- Bearings
- Chains
- Canning
- Gears
- Valves
- Circulating Oil
- Airline Lubricant

## Characteristics

- Reduce varnish and deposit build-up
- Low evaporation rate
- Wide temperature range
- Substantial reduction in make-up oil
- Anti-wear protection

## Typical Properties

WearGuard™ D-A SYN FQH Series	ASTM Test	WearGuard™ D-A FQH 22	WearGuard™ D-A FQH 32	WearGuard™ D-A FQH 46	WearGuard™ D-A FQH 68	WearGuard™ D-A FQH 100	WearGuard™ D-A FQH 150
ISO Viscosity	D2422	22	32	46	68	100	150
Viscosity, cSt.	D445 40 °C	22	31.4	46.0	68.8	93.6	147
	D445 100 °C	4.5	5.6	7.9	10.5	12.9	17.6
Viscosity Index	D2270	116	117	127	141	136	132
Pour Point	D97 °C	-60	-60	-54	-48	-42	-37
	D97 °F	-76	-76	-65	-55	-44	-35
Flash Point	D92 °C	240	240	246	240	232	238
	D92 °F	465	465	475	465	450	460
Specific Gravity	D1298 °C	0.82	0.82	0.83	0.84	0.84	0.85
Copper Corrosion	D130	1B	1B	1B	1B	1B	1B
Foaming Sequence	D892	Nil	Nil	Nil	Nil	Nil	Nil



801 Edwards Drive Lebanon, IN 46052  
 1-800-OIL-LUBE (1-800-645-5823)  
 (317) 923-5321 (765) 482-3065 FAX  
[www.dalube.com](http://www.dalube.com) [dalube@dalube.com](mailto:dalube@dalube.com)

DA-SYNFQH Series rev 7/2013

The information in this bulletin is, to the best of our knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

© 2013, D-A Lubricant Company, Inc.